

APPENDIX 2

Appendix to Figure 6A

Gold and arsenic content in samples from Złoty Stok and Bardo Śląskie

Location	SAMPLE ID	Au [ppm]	As [%]
ZŁOTY STOK	M-16 ZSt 31	40	17.35
	S-61	3.43	8.33
	S-64	5.8	8.18
	S-65	2.23	3.19
	S-66	5.5	11.8
	S-68	3.43	7.27
	S-69	10.8	13.87
	S-71	1.14	3.63
	S-72	0.095	0.33
	S-73	3.1	10.18
	S-63	4.15	9.46
	MS-19	5.4	7.2
	S-70	0.49	1.41
	M-15 ZSt 29	5.5	18.87
	M-17 ZSt 26	5.4	9.724
	M-18 Górń pow. 97	0.073	0.01
	MS-16	1.54	2.4
	MS-17	14.4	14.16
	MS-18	0.156	0.52
	MS-20	1.13	0.37
	MS-21	0.8	2.82
	ZS 1.2	29	0.00379
	ZLS 1.1	0.0825	0.000398
	ZLS 1.3	0.0467	0.0594
	ZLS 2.1	0.0108	0.0928
	ZLS 2.2	0.0198	0.081
	ZLS 2.3	4.39	0.00246
	ZLS 2.4	0.207	0.00023
	ZLS 2.5	1.41	0.0011
	ZSM5	1.72	1.9779
	ZSM7	0.894	0.0745
	ZSM8	0.511	1.1362
	ZSM12	0.042	0.0459
	ZSM13	0.169	0.5273
	ZSM14	0.134	0.0468
	ZSM15	0.302	1.2722
	ZSM16	0.177	0.0127
	ZSM17	0.46	2.7341
	ZSM20	0.765	4.4311
	ZSM21	0.134	0.0348
	ZSM22	0.892	5.5418
	ZSL2	5.4	7.2608
	ZSL4	5.5	9.2386
	ZSL36	2.33	4.4408
	ZSL38	8.22	7.0718
	ZSL39	10.9	10.5903
	ZSL40	4.32	1.6319
	ZSL41	7.26	5.3852
	ZSL42	6.31	5.9599
	ZSL43	1.61	1.3886
ZSL44	9.36	9.2664	
ZSL45	6.45	8.3216	
ZSL46	1.38	1.5359	
ZSL47	1.03	1.9392	
ZSL48	11.1	44.1327	
ZSL49	13.1	16.6451	
ZSL50	0.993	3.2085	
ZSL51	1.21	2.2608	
ZSL52	5.99	9.4932	
ZSL54	4.27	7.7715	
ZSL55	1.03	3.5989	
ZSL56	6.48	6.2721	
ZSL57	2.88	3.8647	
ZSL58	19.6	45.0552	
ZSL59	10.6	14.7103	
ZSL60	0.967	1.425	
ZSL61	0.221	0.5106	
ZSL62	2.76	1.6243	
ZSL63	1.92	1.6289	
ZSL64	0.006	0.0232	
ZSL65	0.336	0.5738	
ZSL66	4.64	5.2709	
ZSL67	0.041	0.0675	
BARDO S.	M-27 Bardo13/SM15	6920	97000
	MS-13a	6120	107000
	MS-13b	1070	300
	MS-13c	90	160
	MS-13d	47	140