

APPENDIX 7

Progressive steps of tektite abrasion during cycle no. 7

Cycle	Tektite	Distance (km)	Weight (g)	Weight loss (g)	Weight loss (%)	
CYCLE NO. 7	moldavite	Primary tektite	1.616	0	0.000	
		0-2	0.624	0.991	61.378	
		2-4	0.458	0.165	26.572	
		4-6	0.375	0.082	18.034	
	bediasite	Primary tektite	1.49	0	0.000	
		0-2	0.629	0.86	57.749	
		2-4	0.479	0.15	23.892	
		4-6	0.397	0.082	17.117	
	indochinite	Primary tektite	1.362	0	0.000	
		0-2	0.565	0.796	58.485	
		2-4	0.425	0.139	24.683	
		4-6	0.342	0.082	19.482	
	Libyan Desert Glass	Primary tektite	1.415	0	0.000	
		0-2	0.757	0.657	46.432	
		2-4	0.603	0.154	20.432	
		4-6	0.509	0.093	15.521	
		6-8	0.461	0.047	9.324	

See text for comments and explanations
(see also Tab. 2, Fig. 4)