

## APPENDIX 6

Progressive steps of tektite abrasion during cycle no. 6

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 6	moldavite	Primary tektite	1.269	0	0.000
		0-2	0.649	0.619	48.789
		2-4	0.549	0.1	15.442
		4-6	0.479	0.07	12.792
		6-8	0.429	0.049	10.275
		8-10	0.393	0.036	8.465
	bediasite	Primary tektite	1.401	0	0.000
		0-2	0.747	0.653	46.643
		2-4	0.606	0.14	18.853
		4-6	0.529	0.076	12.649
		6-8	0.477	0.052	9.854
		8-10	0.441	0.035	7.523
	indochinite	Primary tektite	1.533	0	0.000
		0-2	0.773	0.759	49.538
		2-4	0.598	0.175	22.695
		4-6	0.492	0.105	17.653
		6-8	0.434	0.057	11.704
		8-10	0.397	0.036	8.483
	Libyan Desert Glass	Primary tektite	1.38	0	0.000
		0-2	0.872	0.507	36.753
		2-4	0.717	0.154	17.743
		4-6	0.630	0.087	12.223
		6-8	0.563	0.066	10.512
		8-10	0.51	0.053	9.423

See text for comments and explanations  
(see also Tab. 2, Fig. 3)