

## APPENDIX 5

Progressive steps of tektite abrasion during cycle no. 5

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 5	moldavite	Primary tektite	1.588	0	0.000
		0-2	0.724	0.863	54.359
		2-4	0.573	0.151	20.835
		4-6	0.471	0.102	17.899
		6-8	0.417	0.053	11.362
	bediasite	Primary tektite	1.475	0	0.000
		0-2	0.713	0.761	51.643
		2-4	0.546	0.166	23.321
		4-6	0.466	0.08	14.692
		6-8	0.417	0.049	10.542
	indochinite	Primary tektite	1.335	0	0.000
		0-2	0.601	0.733	54.927
		2-4	0.453	0.148	24.685
		4-6	0.364	0.088	19.512
	Libyan Desert Glass	Primary tektite	1.451	0	0.000
		0-2	0.862	0.588	40.532
		2-4	0.701	0.161	18.754
		4-6	0.61	0.09	12.846
		6-8	0.545	0.065	10.643
		8-10	0.499	0.046	8.522

See text for comments and explanations  
(see also Tab. 2, Fig. 3).