

APPENDIX 4

Progressive steps of tektite abrasion during cycle no. 4

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 4	moldavite	Primary tektite	1.476	0	0.000
		0-2	0.609	0.866	58.698
		2-4	0.46	0.148	24.379
		4-6	0.381	0.079	17.142
		6-8	0.338	0.043	11.472
	bediasite	Primary tektite	1.539	0	0.000
		0-2	0.697	0.841	54.649
		2-4	0.548	0.149	21.481
		4-6	0.455	0.092	16.835
	indochinite	Primary tektite	1.306	0	0.000
		0-2	0.58	0.725	55.583
		2-4	0.447	0.132	22.832
		4-6	0.378	0.068	15.357
	Libyan Desert Glass	Primary tektite	1.401	0	0.000
		0-2	0.79	0.61	43.586
		2-4	0.652	0.137	17.382
		4-6	0.558	0.094	14.456
		6-8	0.494	0.063	11.432

See text for comments and explanations
(see also Table 2 and Fig. 2)