

APPENDIX 3

Progressive steps of tektite abrasion during cycle no. 3

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]	
CYCLE NO. 3	moldavite	Primary tektite	1.309	0	0.000	
		0-2	0.703	0.605	46.274	
		2-4	0.581	0.122	17.362	
		4-6	0.495	0.085	14.731	
		6-8	0.438	0.057	11.562	
		8-10	0.395	0.043	9.847	
	bediasite	Primary tektite	1.441	0	0.000	
		0-2	0.0812	0.628	43.589	
		2-4	0.683	0.129	15.899	
		4-6	0.613	0.07	10.289	
		6-8	0.561	0.052	8.524	
		8-10	0.524	0.036	6.479	
	indochinite	Primary tektite	1.693	0	0.000	
		0-2	0.890	0.802	47.375	
		2-4	0.716	0.174	19.582	
		4-6	0.611	0.104	14.592	
		6-8	0.546	0.065	10.672	
		8-10	0.517	0.028	5.276	
	Libyan Desert Glass	Primary tektite	1.118	0	0.000	
		0-2	0.753	0.364	32.643	
		2-4	0.642	0.11	14.643	
		4-6	0.575	0.067	10.536	
		6-8	0.525	0.049	8.567	
8-10		0.492	0.033	6.324		

See text for comments and explanations
(see also Table 2 and Fig. 2)