

APPENDIX 9

Progressive steps of tektite abrasion during cycle no. 9

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 9	moldavite	Primary tektite	1.447	0	0.000
		0-2	0.704	0.742	51.285
		2-4	0.566	0.137	19.574
		4-6	0.487	0.079	14.068
	bediasite	Primary tektite	1.271	0	0.000
		0-2	0.628	0.642	50.534
		2-4	0.492	0.136	21.638
		4-6	0.424	0.067	13.743
		6-8	0.374	0.05	11.843
	indochinite	Primary tektite	1.358	0	0.000
		0-2	0.63	0.727	53.582
		2-4	0.481	0.148	23.621
		4-6	0.406	0.074	15.543
		6-8	0.363	0.042	10.521
	Libyan Desert Glass	Primary tektite	1.407	0	0.000
		0-2	0.824	0.582	41.425
		2-4	0.671	0.152	18.532
		4-6	0.581	0.09	13.423
		6-8	0.513	0.068	11.733
		8-10	0.461	0.051	10.097

See text for comments and explanations
(see also Tab. 2, Fig. 4).