

## APPENDIX 10

Progressive steps of tektite abrasion during cycle no. 10

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 10	moldavite	Primary tektite	1.513	0	0.000
		0-2	0.374	1.138	75.267
		2-4	0.243	0.13	34.858
	bediasite	Primary tektite	1.439	0	0.000
		0-2	0.506	0.932	64.836
		2-4	0.356	0.149	29.632
		4-6	0.281	0.074	20.834
	indochinite	Primary tektite	1.484	0	0.000
		0-2	0.555	0.928	62.583
		2-4	0.411	0.143	25.837
		4-6	0.325	0.086	21.074
	Libyan Desert Glass	Primary tektite	1.416	0	0.000
		0-2	0.703	0.712	50.326
		2-4	0.544	0.158	22.543
		4-6	0.466	0.078	14.438
		6-8	0.415	0.05	10.765

See text for comments and explanations  
(see also Tab. 2, Fig. 5)