

APPENDIX 15

Progressive steps of tektite abrasion during cycle no. 15

Cycle	Tektite	Distance [km]	Weight [g]	Weight loss [g]	Weight loss [%]
CYCLE NO. 15	moldavite	Primary tektite	1.487	0	0.000
		0-2	0.604	0.882	59.364
		2-4	0.442	0.161	26.792
		4-6	0.363	0.078	17.843
	bediasite	Primary tektite	1.559	0	0.000
		0-2	0.648	0.91	58.421
		2-4	0.469	0.178	27.582
	indochinite	Primary tektite	1.534	0	0.000
		0-2	0.591	0.942	61.473
		2-4	0.416	0.174	29.483
		4-6	0.327	0.089	21.483
	Libyan Desert Glass	Primary tektite	1.433	0	0.000
		0-2	0.712	0.72	50.258
		2-4	0.554	0.158	22.233
		4-6	0.473	0.08	14.599
		6-8	0.419	0.054	11.491

See text for comments and explanations
(see also Tab. 2, Fig. 6)